



6010 N. Powerline Road, Ft. Lauderdale, FL 33309  
954-772-0300 • acrylux.com

## PRODUCT DATA

### ***FIB CAULK***

<b>PRODUCT NAME:</b>	Acrylux Fib Caulk
<b>PRODUCT NUMBERS:</b>	FIBQ, FIB1, FIB5
<b>DESCRIPTION:</b>	A waterproof fibrous elastomeric patching compound.
<b>SUGGESTED USES:</b>	Patching roofs, exterior walls, stucco, roof tile, banding, brick, all other masonry surfaces, and as a tile fill compound. Recommended for repairing and maintaining the Acrylux Waterproofing System, caulking seams in corrugated and standing seam metal roofs, and asphalt shingle tab sealing.
<b>COLORS:</b>	Off white
<b>FINISH:</b>	Light texture
<b>VEHICLE TYPE:</b>	Elastomeric
<b>SOLVENT TYPE:</b>	Water
<b>VOC:</b>	gm/l 75
<b>FLASH POINT:</b>	Non-flammable
<b>WEIGHT PER GALLON:</b>	8 lbs.
<b>SPECIFIC GRAVITY:</b>	1.3
<b>THICKNESS:</b>	3/16"
<b>COVERAGE:</b>	Varies according to application and crack widths.
<b>VISCOSITY:</b>	Butter grade
<b>RECOMMENDED DRY TIME:</b>	4 to 6 hours in direct sunlight; dry times may vary depending on air temperature, wind, humidity and applied thickness.
<b>LIMITATIONS:</b>	Not for use under ponding water or below grade applications. Not for rusted surfaces.
<b>SURFACE PREPARATION:</b>	<b><i>For masonry:</i></b> Remove all loose paint, dirt, mildew and chalk by high pressure water cleaning or other methods to obtain a sound surface. Seal any remaining chalk with AC64 primer/sealer.
<b>MIXING:</b>	No mixing necessary.

**SHELF LIFE:** 2 years

**PACKAGING:** 1 gallon, 5 gallon

<b>MECHANICAL PROPERTIES:</b>	Test Temperature	76F
	Tensile Strength (max stress) lbs/sq inch	113
	Tensile Strength (break)lbs/sq inch	117
	% Elongation (max stress)	910
	% Elongation (Fail)	1035
	% Recovery after 25% Elongation	83

**APPLICATION:** This product is a butter grade and may be applied by brush or putty knife. To apply by brush, scoop FIB Caulk with a semi stiff brush and apply to surface. Once caulk is applied to the surface, use brush to spread the FIB over the space or crack. It is not necessary to V-cut cracks when using this product; however, joint tape may reinforce some larger repairs.