



6010 N. Powerline Road, Ft. Lauderdale, FL 33309
954-772-0300 • acrylux.com

WATERPROOFING INSTRUCTIONS

WATERPROOFING A PITCHED GRAVEL ROOF

1. Sweep away most of loose gravel.
2. Apply the gravel-lock of AC64 and water.
3. Apply two (2) coats of Mastic.
4. Apply the finish coat of Roof Flat or Roof Gloss Paint.

- **Preparation:** Sweep away most of loose gravel so that the remaining gravel is no more than a ½" thick. If remaining gravel appears to be heavily mildewed (dark in color), apply a chlorox and water mixture (5 to 1 ratio) to all remaining gravel. Let dry for 24 hours.
- **Gravel-Locking:** Mix 5 gallons of AC64 with 5 gallons of water and flood the complete roof so that the mixture is at least ½ the height of the gravel. Let dry for 24 hours. Note: Direct sunlight is needed for 4 to 6 hours.
- **Mastic:** Roll 2 coats of Mastic to the entire surface and allow it to dry 24 hours between coats.
- **Paint:** After 24 hours apply the finish coat of paint – Roof Flat or Roof Gloss.

Coverage:

- AC64** - approximately 300 square feet per 5 gallons.
- Mastic** - approximately 80-100 square feet per gallon.
- Paint** - approximately 150 square feet per gallon.